



BRICKWORK AVAILABLE SIZES

Sizes	Type	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
3x12	Porcelain	Non-Rectified	Matte	5/16"	11.63	48	Min. 3/16"

BRICKWORK TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction **	BOT 3000 test	≥0.42	≥0.42
Resistance to freeze/thaw cycling *	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage ± 0.4% or ± 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage ± 0.4% or ± 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1



PRODUCT DESCRIPTION

[Home](#) / [Porcelain & Ceramic Tile](#) / Brickwork















BRICKWORK

\$0.00

- [Description](#)
- [Additional information](#)

1-2 WEEK LEAD TIME

AVAILABLE COLORS

Black
Cotto
Dark
Red
Sand
White

Please contact the office for availability. [402-475-1300](tel:402-475-1300)

RECOMMENDED INSTALLATIONS

Wall

Floor

SHARE THIS STYLE



[GENERATE PDF](#)

ADDITIONAL INFORMATION

Color	Beige & Cream , Black , Brown , Red & Orange , White
Material	Decorative , Stone
Finish	Matte
Price	\$\$

Brickwork quantity

Add to cart

SKU: brickwork

Categories: [Glass & Accent Tile](#), [Porcelain & Ceramic Tile](#)

BRICKWORK AVAILABLE SIZES

Sizes	Type	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
3x12	Porcelain	Non-Rectified	Matte	5/16"	11.63	48	Min. 3/16"

BRICKWORK TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction **	BOT 3000 test	≥0.42	≥0.42
Resistance to freeze/thaw cycling *	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage ± 0.4% or ± 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage ± 0.4% or ± 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1

RELATED PRODUCTS



ACID

\$0.00



TIMBER

\$0.00



MANDALAY

\$0.00