





CANTE AVAILABLE SIZES

Sizes	Type	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
12x24	Porcelain	Non-Rectified	Matte	3/8"	15.49	8	
12x12	Porcelain	Mosaic 2x2	Matte	3/8"	9.69	10	
3x24	Porcelain		Matte	3/8"			


FIFTH AVENUE TILE PERFORMANCE DATA



Physical Properties	Standard	Results
Dynamic Coefficient of Friction	D.C.O.F. > 0.42	≥ 0.42
Water Absorption	ANSI A137.1	≤ 0.5%
Resistance to freeze/thaw cycling	ASTM C1026	Resistant
Warpage (diagonal)	Warpage ± 0.4% or ± 0.07 in.	Comply with ANSI A137.1
Warpage (edge)	Warpage ± 0.4% or ± 0.05 in.	Comply with ANSI A137.1
Chemical Resistance (Acid & Bases) (Household Chemicals)	ASTM C650	Unaffected
Thickness	ASTM C499	Comply with ANSI A137.1
Wedging	± 0.25% or ± 0.03 in	Comply with ANSI A137.1



PRODUCT DESCRIPTION

[Home](#) / [Porcelain & Ceramic Tile](#) / Fifth Avenue





FIFTH AVENUE

\$0.00

- [Description](#)
- [Additional information](#)

1-2 WEEK LEAD TIME

AVAILABLE COLORS

Concrete
White

Please contact the office for availability. [402-475-1300](tel:402-475-1300)

RECOMMENDED INSTALLATIONS

Wall
Floor
Exterior

SHARE THIS STYLE



[GENERATE PDF](#)

ADDITIONAL INFORMATION

Color	Brown, Gray, Black, White
Material	Wood, Stone, Concrete, Decorative, 3D Wall
Price	\$
Color	Grey , White
Material	Concrete

Fifth Avenue quantity

1

Add to cart

SKU: fifth-avenue

Categories: [Porcelain & Ceramic Tile](#), [Trade Professionals](#)

CANTE AVAILABLE SIZES

Sizes	Type	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
12x24	Porcelain	Non-Rectified	Matte	3/8"	15.49	8	
12x12	Porcelain	Mosaic 2x2	Matte	3/8"	9.69	10	
3x24	Porcelain		Matte	3/8"			

FIFTH AVENUE TILE PERFORMANCE DATA

Physical Properties	Standard	Results
Dynamic Coefficient of Friction	D.C.O.F. > 0.42	≥ 0.42
Water Absorption	ANSI A137.1	≤ 0.5%
Resistance to freeze/thaw cycling	ASTM C1026	Resistant
Warpage (diagonal)	Warpage ± 0.4% or ± 0.07 in.	Comply with ANSI A137.1
Warpage (edge)	Warpage ± 0.4% or ± 0.05 in.	Comply with ANSI A137.1
Chemical Resistance (Acid & Bases) (Household Chemicals)	ASTM C650	Unaffected
Thickness	ASTM C499	Comply with ANSI A137.1
Wedging	± 0.25% or ± 0.03 in	Comply with ANSI A137.1

RELATED PRODUCTS



PULPIS

\$0.00



SARK STEEL

\$0.00



BERSE

\$0.00