STONEWORKS AVAILABLE SIZES

Sizes	Type	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
12x24	Porcelain	Rectified	Matte		13.56	7	
12x24	Porcelain	Rectified	Glossy		13.11	7	
24x24	Porcelain	Rectified	Matte		11.64	3	
24x24	Porcelain	Rectified	Glossy		11.24	3	
24x48	Porcelain		Matte				
3x24 Bullnose	Porcelain		Matte			10	
6x12 Covebase	Porcelain		Matte			20	
12x12	Porcelain	Mosaic 2x6 Brickset	Matte		9.69	10	
12x12	Porcelain	Mosaic Basketweave Mosaic	Matte		9.69	10	
10x12	Porcelain	Mosaic Hex	Matte		8.07	10	
10x12	Porcelain	Mosaic Hex	Glossy		8.07	10	
12x12	Porcelain	Mosaic 2x2	Glossy			10	
1.2x24	Porcelain	Decorative Accent	Matte			6	
1.8x24	Porcelain	Decorative Accent	Matte			4	
1.88x24	Porcelain	Rectified	Glossy			10	
1.88x1.88	Porcelain	Dot	Glossy			70	

STONEWORKS MATTE TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction	BOT 3000 test	≥0.42	≥0.42
Resistance to freeze/thaw cycling	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage ± 0.4% or ± 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage ± 0.4% or ± 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1

STONEWORKS GLOSSY TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction	BOT 3000 test	≥0.42	<0.42
Resistance to freeze/thaw cycling	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage ± 0.4% or ± 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage ± 0.4% or ± 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1

Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1

PRODUCT DESCRIPTION

STONEWORKS

$0.00

- Description
- Additional information

1-2 WEEK LEAD TIME

AVAILABLE COLORS

Calacatta
Frappuccino
Graphite
Statuario

Please contact the office for availability. 402-475-1300

RECOMMENDED INSTALLATIONS

Floor
Wall
Exterior

SHARE THIS STYLE

GENERATE PDF

ADDITIONAL INFORMATION

Color	Brown, Grey, White
Material	Stone
Finish	Glossy, Matte
Price	$

Stoneworks quantity

1

Add to cart

SKU: stoneworks

Categories: Porcelain & Ceramic Tile, Trade Professionals

STONEWORKS AVAILABLE SIZES

Sizes	Type	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
12x24	Porcelain	Rectified	Matte		13.56	7	
12x24	Porcelain	Rectified	Glossy		13.11	7	
24x24	Porcelain	Rectified	Matte		11.64	3	
24x24	Porcelain	Rectified	Glossy		11.24	3	
24x48	Porcelain		Matte				
3x24 Bullnose	Porcelain		Matte			10	
6x12 Covebase	Porcelain		Matte			20	
12x12	Porcelain	Mosaic 2x6 Brickset	Matte		9.69	10	
12x12	Porcelain	Mosaic Basketweave Mosaic	Matte		9.69	10	
10x12	Porcelain	Mosaic Hex	Matte		8.07	10	
10x12	Porcelain	Mosaic Hex	Glossy		8.07	10	
12x12	Porcelain	Mosaic 2x2	Glossy			10	
1.2x24	Porcelain	Decorative Accent	Matte			6	
1.8x24	Porcelain	Decorative Accent	Matte			4	
1.88x24	Porcelain	Rectified	Glossy			10	
1.88x1.88	Porcelain	Dot	Glossy			70	

STONEWORKS MATTE TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction	BOT 3000 test	≥0.42	≥0.42
Resistance to freeze/thaw cycling	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage ± 0.4% or ± 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage ± 0.4% or ± 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1

STONEWORKS GLOSSY TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction	BOT 3000 test	≥0.42	<0.42
Resistance to freeze/thaw cycling	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage ± 0.4% or ± 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage ± 0.4% or ± 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1

RELATED PRODUCTS

- ### CORCHO

  $0.00

- ### METRO

  $0.00

- ### GLACIER

  $0.00