






TAPESTRY AVAILABLE SIZES


Sizes	Туре	Style	Finish	Thickness	Sqft/Carton	Pieces/Box	Recommended Grout Joint
12x24	Porcelain	Rectified	Matte		13.56	7	
6x24	Porcelain	Rectified	Matte		3.88	4	
0.8x24	Porcelain	Rectified	Matte			10	
0.8x0.8	Porcelain	Rectified	Matte				
6x12 Covebase	Porcelain	Rectified	Matte			20	

TAPESTRY TILE PERFORMANCE DATA


Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction	BOT 3000 test	≥0.42	≥0.42
Resistance to freeze/thaw cycling	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage \pm 0.4% or \pm 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage \pm 0.4% or \pm 0.07 in	Comply with ANSI A137.1
Wedging	C502	± 0.25% or ± 0.03 in	Comply with ANSI A137.1
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1



PRODUCT DESCRIPTION







TAPESTRY

\$0.00

- <u>Description</u>
- Additional information

1-2 WEEK LEAD TIME

AVAILABLE COLORS

Coffee Dark Grey Ivory Silver White

Please contact the office for availability. 402-475-1300

RECOMMENDED INSTALLATIONS

Floor Wall Exterior

SHARE THIS STYLE



GENERATE PDF

ADDITIONAL INFORMATION

MaterialFabricFinishMattePrice\$

Tapestry quantity

Add to cart

SKU: tapestry

Categories: Porcelain & Ceramic Tile, Trade Professionals

TAPESTRY AVAILABLE SIZES


Sizes	Type Style	Finish Thicknes	s Sqft/Cartoi	n Pieces/Box	Recommended Grout Joint
12x24	Porcelain Rectified	Matte	13.56	7	
6x24	Porcelain Rectified	Matte	3.88	4	
0.8x24	Porcelain Rectified	Matte		10	
0.8x0.8	Porcelain Rectified	Matte			
6x12 Covebase	Porcelain Rectified	Matte		20	

TAPESTRY TILE PERFORMANCE DATA

Physical Properties	Test ASTM	North American Standard A137.1	Results
Water Absorption	C373	≤0.5%	Comply with ANSI A137.1
DCOF Average Dynamic Coefficient of Friction	BOT 3000 tes	t ≥0.42	≥0.42
Resistance to freeze/thaw cycling	C1026	As reported	Resistant
Warpage (edge)	C485	Warpage \pm 0.4% or \pm 0.05 in	Comply with ANSI A137.1
Warpage (diagonal)	C485	Warpage \pm 0.4% or \pm 0.07 in	Comply with ANSI A137.1
Wedging	C502	\pm 0.25% or \pm 0.03 in	Comply with ANSI A137.1

Physical Properties	Test ASTM	North American Standard A137.1	Results
Chemical Resistance	C650	As reported	Unaffected
Breaking Strength	C648	250 lbf or greater	Comply with ANSI A137.1
Thickness	C499	Range: 0.04 in	Comply with ANSI A137.1

RELATED PRODUCTS



BRICK

\$0.00



METRO

\$0.00



CORCHO

\$0.00